

# Titalon® 2330AGF

Polyamide 66

Titan Plastics Compounds Co., Ltd.

## Message:

Titalon®2330AGF is a polyamide 66 (nylon 66) material, which contains a 33% glass fiber reinforced material. This product is available in the Asia-Pacific region.

Titalon®The main characteristics of 2330AGF are:

flame retardant/rated flame

high strength

anti-warping

| General Information                                        |                                                       |                   |             |
|------------------------------------------------------------|-------------------------------------------------------|-------------------|-------------|
| Filler / Reinforcement                                     | Glass fiber reinforced material, 33% filler by weight |                   |             |
| Features                                                   | Low warpage                                           |                   |             |
|                                                            | High strength                                         |                   |             |
| Appearance                                                 | Black                                                 |                   |             |
| Physical                                                   | Nominal Value                                         | Unit              | Test Method |
| Density                                                    | 1.39                                                  | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage <sup>1</sup> (3.00 mm)                   | 0.30 - 0.80                                           | %                 |             |
| Mechanical                                                 | Nominal Value                                         | Unit              | Test Method |
| Tensile Stress                                             | 175                                                   | MPa               | ISO 527-2   |
| Tensile Strain (Break)                                     | > 2.5                                                 | %                 | ISO 527-2   |
| Flexural Modulus                                           | 11000                                                 | MPa               | ISO 178     |
| Flexural Stress                                            | 270                                                   | MPa               | ISO 178     |
| Impact                                                     | Nominal Value                                         | Unit              | Test Method |
| Charpy Notched Impact Strength                             | 10                                                    | kJ/m <sup>2</sup> | ISO 179/1eA |
| Thermal                                                    | Nominal Value                                         | Unit              | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed)          | 250                                                   | °C                | ISO 75-2/A  |
| Electrical                                                 | Nominal Value                                         | Unit              | Test Method |
| Surface Resistivity                                        | 1.0E+14                                               | ohms              | IEC 60093   |
| Volume Resistivity                                         | 1.0E+14                                               | ohms · cm         | IEC 60093   |
| Flammability                                               | Nominal Value                                         | Unit              | Test Method |
| Flame Rating                                               | HB                                                    |                   | UL 94       |
| Injection                                                  | Nominal Value                                         | Unit              |             |
| Drying Temperature                                         | 80.0 - 100                                            | °C                |             |
| Drying Time                                                | 4.0                                                   | hr                |             |
| Processing (Melt) Temp                                     | 260 - 290                                             | °C                |             |
| Mold Temperature                                           | 60.0 - 100                                            | °C                |             |
| Injection instructions                                     |                                                       |                   |             |
| Injection Pressure: 30 to 70%Injection Velocity: 30 to 60% |                                                       |                   |             |

## NOTE

1. 50x70x3 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

