

Sindustris PC SC3155

Polycarbonate

Sincerity Australia Pty Ltd.

Message:

Sindustris PC SC3155 is a Polycarbonate (PC) material filled with 15% glass fiber. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris PC SC3155 are:

Flame Rated

Chemical Resistant

Good Aesthetics

Good Dimensional Stability

Good Toughness

Typical applications include:

Electrical/Electronic Applications

Housings

General Information			
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Features	General Purpose		
	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Surface Finish		
	Good Toughness		
Uses	Cell Phones		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	47.1	MPa	ASTM D638
Tensile Elongation ² (Yield, 3.20 mm)	25	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	3040	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	88.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	220	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	137	°C	ASTM D648
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	280 to 295	°C	
Middle Temperature	285 to 300	°C	
Front Temperature	290 to 305	°C	
Nozzle Temperature	290 to 305	°C	
Processing (Melt) Temp	290 to 310	°C	
Mold Temperature	90.0 to 110	°C	
Back Pressure	0.981 to 3.92	MPa	
Screw Speed	40 to 70	rpm	
NOTE			
1.	5.0 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		
4.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT