

Mytex® 8224(L)(W)

Polypropylene

Mytex Polymers

Message:

MYTEX 8224(L)(W) is a non-filled compounded polypropylene produced for automotive applications.

General Information			
Uses	Automotive Applications		
	Automotive Exterior Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.895	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	65		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	20.0	MPa	ISO 527-2/50
Flexural Modulus - Tangent ¹	1000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	16	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	78.0	°C	ISO 75-2/B
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT