

DOMAMID® 66G15FC

Polyamide 66

DOMO Engineering Plastics SPA

Message:

Polyamide 66, 15% glass fiber reinforced, for injection moulding. Food contact compliant

General Information			
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Features	Food Contact Acceptable		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Viscosity Number	145	cm ³ /g	ISO 307
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ISO 527-2/1
Tensile Stress (Break)	125	MPa	ISO 527-2/5
Tensile Strain (Break)	2.5	%	ISO 527-2/5
Flexural Modulus ¹	5100	MPa	ISO 178
Flexural Stress ²	195	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	6.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	35	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	245	°C	ISO 75-2/B
1.8 MPa, Unannealed	230	°C	ISO 75-2/A
Vicat Softening Temperature	245	°C	ISO 306/B50
Melting Temperature	260	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	

Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	90.0 to 110	°C
NOTE		
1.	2.0 mm/min	
2.	2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT