

HOPELEX TC-8001G

Polycarbonate

Lotte Chemical Corporation

Message:

Thermal conductive, graphite filled, medium viscosity, easy mold release

Non-brominated, non-chlorinated flame retardant

Available in opaque color only

General Information			
Filler / Reinforcement	Graphite Powder		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Good Mold Release		
	Medium Viscosity		
	Thermally Conductive		
Uses	Electrical Housing		
Appearance	Opaque		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	46.1	MPa	ASTM D638
Flexural Modulus ²	5300	MPa	ASTM D790
Flexural Strength ³ (Yield)	65.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	140	°C	ASTM D648
Thermal Conductivity ⁴	> 0.60	W/m/K	
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Max Regrind	20	%	
Hopper Temperature	60.0 to 80.0	°C	

Rear Temperature	290 to 310	°C
Middle Temperature	280 to 300	°C
Front Temperature	270 to 290	°C
Nozzle Temperature	280 to 300	°C
Processing (Melt) Temp	290 to 310	°C
Mold Temperature	60.0 to 90.0	°C

NOTE

- | | |
|----|-----------------|
| 1. | 50 mm/min |
| 2. | 10 mm/min |
| 3. | 10 mm/min |
| 4. | Hot Wire Method |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

