

LEXAN™ SLX2271T resin

Polycarbonate

SABIC Innovative Plastics Europe

Message:

Low viscosity PC copolymer blend with enhanced UV stabilization and added release agent. V2 rated. Available in transparent and tinted colors

General Information			
Additive	demoulding UV stabilizer		
Features	Low viscosity Copolymer Good UV resistance Good demoulding performance		
Appearance	Available colors Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	18	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.35	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Outdoor Suitability	f2		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2400	MPa	ASTM D638
--	2300	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	65.0	MPa	ASTM D638
Yield	67.0	MPa	ISO 527-2/50
Fracture ³	67.0	MPa	ASTM D638
Fracture	70.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.0	%	ASTM D638

Yield	6.0	%	ISO 527-2/50
Fracture ⁵	> 100	%	ASTM D638
Fracture	> 100	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2450	MPa	ASTM D790
-- ⁷	2450	MPa	ISO 178
Flexural Stress			
--	96.0	MPa	ISO 178
Yield, 50.0mm span ⁸	96.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	15	kJ/m ²	ISO 179/1eA
23°C	65	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰ (23°C)	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	130	J/m	ASTM D256
23°C	780	J/m	ASTM D256
-30°C ¹¹	10	kJ/m ²	ISO 180/1A
23°C ¹²	65	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³ (23°C)	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	80.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	124	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁴	124	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	139	°C	ASTM D1525, ISO 306/B50 ¹⁵
--	140	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.00 mm)	V-2		UL 94
Glow Wire Flammability Index (1.50 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	825	°C	IEC 60695-2-13
2.00 mm	825	°C	IEC 60695-2-13
2.50 mm	825	°C	IEC 60695-2-13
3.00 mm	825	°C	IEC 60695-2-13

Optical	Nominal Value	Unit	Test Method
Refractive Index	1.590		ISO 489
Transmittance (2540 μm)	89.0	%	ASTM D1003
Haze (2540 μm)	0.60	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	60.0 - 80.0	°C	
Rear Temperature	260 - 280	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	280 - 310	°C	
Nozzle Temperature	270 - 290	°C	
Processing (Melt) Temp	280 - 310	°C	
Mold Temperature	80.0 - 110	°C	

NOTE

1. 5.0 mm/min
2. Type 1, 50mm/min
3. Type 1, 50mm/min
4. Type 1, 50mm/min
5. Type 1, 50mm/min
6. 1.3 mm/min
7. 2.0 mm/min
8. 1.3 mm/min
9. 80*10*3 sp=62mm
10. 80*10*3 sp=62mm
11. 80*10*3
12. 80*10*3
13. 80*10*3
14. 80*10*4 mm
15. 标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT