

TRIBOCOMP® A-5 TS0

Polyamide 66

EPIC Polymers

Message:

TRIBOCOMP® A-5 TS0 is a Polyamide 66 (Nylon 66) product filled with 45% long glass fiber and 10% ptfe fiber. It is available in Europe.

General Information				
Filler / Reinforcement		Long Glass Fiber,45% Filler by Weight		
		PTFE Fiber,10% Filler by Weight		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.60	--	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.20	--	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	1.2	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2
23°C	16800	13000	MPa	
90°C	11700	--	MPa	
120°C	8800	--	MPa	
Tensile Stress				ISO 527-2
Yield, 23°C	225	170	MPa	
Yield, 90°C	160	--	MPa	
Yield, 120°C	135	--	MPa	
Tensile Strain (Break, 23°C)	2.5	--	%	ISO 527-2
Flexural Modulus (23°C)	14000	10500	MPa	ISO 178
Flexural Stress (23°C)	360	270	MPa	ISO 178
Coefficient of Friction				ASTM D3702
vs. Itself - Dynamic	0.29	--		
vs. Itself - Static	0.23	--		
Wear Factor	14	--	10 ⁻⁸ mm ³ /N·m	ASTM D3702
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	25	--	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	80	--	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	255	--	°C	ISO 75-2/B

1.8 MPa, Unannealed	253	--	°C	ISO 75-2/A
CLTE - Flow (23°C)	2.1E-5	--	cm/cm/°C	ISO 7991
Thermal Conductivity	0.33	--	W/m/K	ISO 22007
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	--	ohms	ASTM D257
Electric Strength	36	--	kV/mm	IEC 60243-1
Comparative Tracking Index	500	--	V	IEC 60112
Extrusion	Dry	Unit		
Cylinder Zone 1 Temp.	270 to 300		°C	
Cylinder Zone 2 Temp.	270 to 300		°C	
Cylinder Zone 3 Temp.	285 to 300		°C	
Cylinder Zone 4 Temp.	285 to 310		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

