

LNP™ THERMOCOMP™ UF008H compound

Polyphthalamide

SABIC Innovative Plastics

Message:

LNP THERMOCOMP* UF008H is a compound based on Polyphthalamide resin containing Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound UF-1008

Product reorder name: UF008H

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.55	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.30	%	ASTM D955
Transverse flow: 24 hours	1.2	%	ASTM D955
Vertical flow direction: 24 hours	1.2	%	ISO 294-4
Flow direction: 24 hours	0.27	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.27	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.42	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	16100	MPa	ASTM D638
--	14300	MPa	ISO 527-2/1
Tensile Strength			
Fracture	237	MPa	ASTM D638
Fracture	205	MPa	ISO 527-2
Tensile Elongation			
Fracture	2.1	%	ASTM D638
Fracture	2.0	%	ISO 527-2
Flexural Modulus			
--	13400	MPa	ASTM D790
--	13800	MPa	ISO 178
Flexural Strength			
--	311	MPa	ASTM D790
--	322	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	85	J/m	ASTM D256
23°C ²	9.0	kJ/m ²	ISO 180/1A

Unnotched Izod Impact			
23°C	870	J/m	ASTM D4812
23°C ³	52	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	5.10	J	ASTM D3763
--	2.50	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	282	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	272	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	2.3E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	2.5E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	2.9E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	3.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121 - 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15	%	
Rear Temperature	310 - 321	°C	
Middle Temperature	316 - 327	°C	
Front Temperature	327 - 338	°C	
Processing (Melt) Temp	316 - 332	°C	
Mold Temperature	138 - 166	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT