

Exelene® LLDPE 1900

Metallocene Linear Low Density Polyethylene

Montachem International, Inc.

Message:

Applications:

Packaging Films, Agricultural Films, General Packaging, Blown Film, Bread Bags

Trash bags, trash can liners, multi layer packaging

Characteristics:

The Exelene resin LLDPE 1900 meets the requirements of section 177.1520, paragraph C, from chapter 21 denominated "Olefin Polymers" from the Code of Federal Regulations of the FDA, to be utilized with direct food contact.

General Information			
Features	Food Contact Acceptable		
	Low Density		
Uses	Bags		
	Food Packaging		
	Food Service Applications		
	Non-specific Food Applications		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520(c)		
Processing Method	Blown Film		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.917	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength ¹			ASTM D882
-- ²	179	MPa	
-- ³	172	MPa	
Films	Nominal Value	Unit	Test Method
Tensile Strength ⁴			
MD : Yield	8.76	MPa	ASTM D882
TD : Yield	8.41	MPa	ASTM D882
MD : Break	45.3	MPa	ASTM D882A
TD : Break	31.8	MPa	ASTM D882A
Tensile Elongation ⁵			ASTM D882A
MD : Break	470	%	
TD : Break	550	%	

Dart Drop Impact ⁶ (38000 μm)	580	g	ASTM D1709A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	119	°C	DSC
Optical	Nominal Value		Test Method
Gloss	42		ASTM D2457
NOTE			
1.	5.1 mm/min		
2.	TD, 1% secant		
3.	MD, 1% secant		
4.	510 mm/min		
5.	510 mm/min		
6.	F50, 66 cm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

