

Stanyl® TE250F3

Polyamide 46
DSM Engineering Plastics

Message:

Stanyl® TE250F3 is a Polyamide 46 (Nylon 46) material filled with 15% glass fiber. It is available in Asia Pacific, Europe, or North America.
Important attributes of Stanyl® TE250F3 are:
Flame Rated
Flame Retardant
Heat Stabilizer

General Information				
UL YellowCard		E43392-235031	E47960-240063	
Filler / Reinforcement		Glass Fiber,15% Filler by Weight		
Additive		Flame Retardant		
		Heat Stabilizer		
Features		Flame Retardant		
		Heat Stabilized		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.52	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.5	--	%	
Flow	1.0	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	8000	--	MPa	ISO 527-2
Tensile Stress (Break)	140	--	MPa	ISO 527-2
Tensile Strain (Break)	3.0	--	%	ISO 527-2
Flexural Modulus	7500	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	6.0	kJ/m ²	
23°C	6.0	10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	40	kJ/m ²	
23°C	40	50	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A

-40°C	6.0	6.0	kJ/m ²	
23°C	6.0	10	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	290	--	°C	ISO 75-2/A
Melting Temperature ¹	295	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	4.0E-5	--	cm/cm/°C	
Transverse	6.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength	30	20	kV/mm	IEC 60243-1
Comparative Tracking Index	175	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.900 mm	V-0	--		
1.50 mm	V-0	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	280 to 320		°C	
Middle Temperature	300 to 320		°C	
Front Temperature	300 to 320		°C	
Nozzle Temperature	300 to 320		°C	
Processing (Melt) Temp	310 to 320		°C	
Mold Temperature	80.0 to 120		°C	
Injection Rate	Moderate-Fast			
Back Pressure	2.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT