# **MBA ABS 4135**

#### Acrylonitrile Butadiene Styrene

### **MBA** Polymers

#### Message:

An easy flowing, post-consumer recycled acrylonitrile-butadiene-styrene copolymer for general use. Standard colors include standard grey (reference 70/15) and standard black (reference 90/04). Other colors may be available upon request.

General Information			
Recycled Content	Yes		
Features	Copolymer		
	Good Flow		
Uses	General Purpose		
Appearance	Black		
	Colors Available		
	Grey		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	7.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	38.0	MPa	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	13	kJ/m²	ISO 180/1A
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Processing (Melt) Temp	210 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Melt Temperature	200 to 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

