

LNP™ THERMOCOMP™ JF006EXZ compound

Polyethersulfone

SABIC Innovative Plastics

Message:

LNP THERMOCOMP JF006EXZ is a compound based on Polyethersulfone resin containing 30% Glass Fiber. Added features of this material include: Easy Molding.

Also known as: LNP* THERMOCOMP* Compound JF-1006 EM

Product reorder name: JF006EXZ

General Information			
UL YellowCard	E121562-101283894		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Moldability		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.30 to 0.50	%	
Across Flow : 24 hr	0.60 to 0.80	%	
Water Absorption (24 hr, 50% RH)	0.21	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Break	140	MPa	ASTM D638
Break	145	MPa	ISO 527-2
Tensile Elongation			
Break	2.6	%	ASTM D638
Break	1.9	%	ISO 527-2
Flexural Modulus			
--	8910	MPa	ASTM D790
--	9700	MPa	ISO 178
Flexural Strength			
--	193	MPa	ASTM D790
--	209	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	78	J/m	ASTM D256
23°C ¹	8.9	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	550	J/m	ASTM D4812
23°C ²	40	kJ/m ²	ISO 180/1U

Instrumented Dart Impact (23°C, Energy at Peak Load)	6.98	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	213	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ³	213	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	360 to 371	°C	
Front Temperature	371 to 382	°C	
Processing (Melt) Temp	354 to 371	°C	
Mold Temperature	138 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

