

OmniTech™ ASA 220

Acrylonitrile Styrene Acrylate
OMNI Plastics, LLC

Message:
General Purpose ASA

General Information			
Features	General Purpose		
Uses	General Purpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (265°C/3.4 kg)	20	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	46.2	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength	65.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	96.1	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (3.18 mm)	HB		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	87.8	°C	
Drying Time	< 4.0	hr	
Suggested Max Moisture	0.040	%	
Rear Temperature	204 to 249	°C	
Middle Temperature	216 to 260	°C	
Front Temperature	216 to 260	°C	
Nozzle Temperature	216 to 260	°C	
Processing (Melt) Temp	216 to 260	°C	
Mold Temperature	26.7 to 60.0	°C	
Back Pressure	0.345 to 0.689	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

