

APICAL 50AV

Thermoset Polyimide

Kaneka Corporation

Message:

APICAL 50AV is a Thermoset Polyimide material. It is available in North America.

Important attributes of APICAL 50AV are:

Flame Rated

Chemical Resistant

Good Dimensional Stability

Good Flexibility

Typical applications include:

Adhesives/Tapes

Electrical/Electronic Applications

Film

Wire & Cable

General Information			
UL YellowCard	E48854-100128664		
Features	Good Chemical Resistance		
	Good Dimensional Stability		
	Good Flexibility		
Uses	Film		
	Insulation		
	Printed Circuit Boards		
	Tape		
Appearance	Natural Color		
Forms	Sheet		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ASTM D1505
Molding Shrinkage - Flow	4.0E-3	%	ASTM D955
Water Absorption (24 hr)	2.9	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Static)	0.50		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	13	μm	
Secant Modulus - 1% Secant, MD	3170	MPa	ASTM D882
Tensile Strength - MD (Break)	241	MPa	ASTM D882
Tensile Elongation - MD (Break)	95	%	ASTM D882
Elmendorf Tear Strength - MD	4.0	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Specific Heat	1100	J/kg/°C	ASTM C351

RTI Elec (0.0125 mm)	240	°C	UL 746
RTI Str (0.0125 mm)	200	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Hot-wire Ignition (HWI) (0.0125 mm)	120	sec	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.125 mm)	V-0		UL 94
Oxygen Index	38	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

