

Bakelite® PF 2400

Phenolic

Hexion Inc.

Message:

Product Description

Phenolic moulding compound, inorganically/organically filled, average heat resistance, increased dimensional stability, dishwasher proof, UL listed moulding compound 1.5 mm / V-0 (ALL)

Application Areas

MCB-housings, cookware fittings, meter covers and bases, knobs/handles

General Information			
Filler / Reinforcement	Organic\Inorganic		
Features	Good Surface Finish		
Uses	Cookware		
	Fittings		
	Handles		
	Housings		
	Knobs		
Processing Method	Compression Molding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.47	g/cm³	ISO 1183
Apparent Density	0.65	g/cm³	ISO 60
Molding Shrinkage			ISO 2577
-- ¹	0.45	%	
-- ²	0.75	%	
Water Absorption - 24h/23C	45.0	mg	ISO 62
Post Shrinkage			ISO 2577
-- ³	0.45	%	
-- ⁴	0.45	%	
Compression Molding Molding Pressure	> 15.0	MPa	
Compression Molding Temperature	160 to 190	°C	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 961/30)	340	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ISO 527-2/1
Tensile Stress	55.0	MPa	ISO 527-2/5
Flexural Modulus	8000	MPa	ISO 178
Flexural Stress ⁵	95.0	MPa	ISO 178

Compressive Stress	250	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (8.0 MPa, Unannealed)	125	°C	ISO 75-2/C
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+11	ohms·cm	IEC 60093
Electric Strength ⁶ (1.00 mm)	25	kV/mm	IEC 60243-1
Relative Permittivity (100 Hz)	9.50		IEC 60250
Dissipation Factor (100 Hz)	0.25		IEC 60250
Comparative Tracking Index (Solution A)	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, All)	V-0		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	60.0 to 75.0	°C	
Nozzle Temperature	80.0 to 100	°C	
Processing (Melt) Temp	80.0 to 100	°C	
Mold Temperature	160 to 190	°C	
Injection Pressure	> 15.0	MPa	
Back Pressure	0.500 to 2.00	MPa	
NOTE			
1.	Compression		
2.	Injection		
3.	Injection		
4.	Compression		
5.	2.0 mm/min		
6.	short term, electrode layout P25mm/P25mm in transformer oil equivalent to IEC 60296		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT