

LNP™ LUBRICOMP™ RN001S compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP LUBRICOMP RN001S is a compound based on Nylon 66 resin containing 2% MOS2. Added features of this material include: Wear Resistant, Heat Stabilized.

Also known as: LNP* LUBRICOMP* Compound NYKON R- HS

Product reorder name: RN001S

General Information			
Additive	Heat Stabilizer		
	Molybdenum Disulfide Lubricant (2%)		
Features	Good Wear Resistance		
	Heat Stabilized		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.16	g/cm ³	ASTM D792
--	1.17	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 24 hr	1.0	%	
Flow : 24 hr	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4140	MPa	ASTM D638
--	3910	MPa	ISO 527-2/1
Tensile Strength			
Yield	84.1	MPa	ASTM D638
Yield	69.0	MPa	ISO 527-2
Break	84.1	MPa	ASTM D638
Break	69.0	MPa	ISO 527-2
Tensile Elongation			
Yield	2.9	%	ASTM D638
Yield	2.1	%	ISO 527-2
Break	3.8	%	ASTM D638
Break	42	%	ISO 527-2
Flexural Modulus			
--	3450	MPa	ASTM D790

--	3400	MPa	ISO 178
Flexural Stress	107	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.75		
vs. Itself - Static	0.55		
Wear Factor - Washer	103	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	27	J/m	ASTM D256
23°C ²	2.8	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1100	J/m	ASTM D4812
23°C ³	54	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Energy at Peak Load)	2.30	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	231	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	223	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	76.7	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	301	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	277 to 288	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

