

Grilamid® L 25 W 40 X

Polyamide 12

EMS-GRIVORY

Message:

Grilamid® L 25 W 40 X is a Polyamide 12 (Nylon 12) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion.

Important attributes of Grilamid® L 25 W 40 X are:

- Flame Rated
- RoHS Compliant
- Plasticized
- Good Flexibility
- High Viscosity

Typical applications include:

- Automotive
- Consumer Goods
- Electrical/Electronic Applications
- Hose/Tubing
- Industrial Applications

General Information				
Additive		Plasticizer		
Features	Good Flexibility			
	Good Impact Resistance			
	High Viscosity			
	Plasticized			
Uses	Automotive Applications			
	Consumer Applications			
	Electrical/Electronic Applications			
	Hydraulic Applications			
	Industrial Applications			
	Pneumatic Applications			
	Tubing			
	Wire & Cable Applications			
RoHS Compliance		RoHS Compliant		
Forms		Granules		
Processing Method		Extrusion		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)			
	Secant Modulus vs. Strain (ISO 11403-1)			
	Shear Modulus vs. Temperature (ISO 11403-1)			
	Viscosity vs. Shear Rate (ISO 11403-2)			
Physical	Dry	Conditioned	Unit	Test Method

Density	1.02	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.2	--	%	
Flow	0.90	--	%	
Water Absorption				ISO 62
Saturation, 23°C	1.4	--	%	
Equilibrium, 23°C, 50% RH	0.70	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	380	360	MPa	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	13	kJ/m ²	
23°C	No Break	No Break		
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	95.0	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	45.0	--	°C	ISO 75-2/A
Melting Temperature ¹	173	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.4E-4	--	cm/cm/°C	
Transverse	1.8E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	--	1.0E+13	ohms·cm	IEC 60093
Electric Strength	--	32	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

