

# GERMAMID B 6 GF 30 SCHWARZ

Polyamide 6

Kunststoff-Kontor-Hamburg GmbH

## Message:

GERMAMID B 6 GF 30 SCHWARZ is a Polyamide 6 (Nylon 6) material filled with 30% glass fiber. It is available in Europe.

| General Information                               |                                  |                   |             |
|---------------------------------------------------|----------------------------------|-------------------|-------------|
| Filler / Reinforcement                            | Glass Fiber,30% Filler by Weight |                   |             |
| Appearance                                        | Black                            |                   |             |
| Forms                                             | Pellets                          |                   |             |
| Physical                                          | Nominal Value                    | Unit              | Test Method |
| Density                                           | 1.35                             | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                                 | 0.20 to 0.70                     | %                 | ISO 294-4   |
| Water Absorption (Saturation, 23°C)               | 2.0                              | %                 | ISO 62      |
| Mechanical                                        | Nominal Value                    | Unit              | Test Method |
| Tensile Modulus                                   | 8500                             | MPa               | ISO 527-2   |
| Tensile Stress (Yield)                            | 165                              | MPa               | ISO 527-2   |
| Tensile Strain (Break)                            | 2.5                              | %                 | ISO 527-2   |
| Impact                                            | Nominal Value                    | Unit              | Test Method |
| Charpy Notched Impact Strength                    | 9.0                              | kJ/m <sup>2</sup> | ISO 179/1eA |
| Charpy Unnotched Impact Strength                  | 40                               | kJ/m <sup>2</sup> | ISO 179/1eU |
| Thermal                                           | Nominal Value                    | Unit              | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 210                              | °C                | ISO 75-2/A  |
| Melting Temperature                               | 218                              | °C                |             |
| Thermal Conductivity                              | 0.28                             | W/m/K             | ISO 8302    |
| Electrical                                        | Nominal Value                    | Unit              | Test Method |
| Surface Resistivity                               | 1.0E+12                          | ohms              | IEC 60093   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT