

DENYL HT 6010

Polyphthalamide

Vamp Tech

Message:

PPA 60% glass fiber reinforced, excellent mechanicals properties, low water absorption, high chemical resistance and excellent operating temperature.

General Information			
Filler / Reinforcement	Glass Fiber,60% Filler by Weight		
Features	Good Chemical Resistance		
	Low to No Water Absorption		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.73	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.050	%	
Across Flow	0.30	%	
Water Absorption (Saturation)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	23000	MPa	ASTM D638
Tensile Strength (Yield)	250	MPa	ASTM D638
Tensile Elongation (Break)	1.6	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	10	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	50	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	280	°C	ASTM D648A
RTI Elec	150	°C	UL 746
RTI Imp	150	°C	UL 746
RTI Str	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Comparative Tracking Index (CTI)	600	V	UL 746
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	330	°C	
Mold Temperature	140	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT