

Shinko-Lac® ABS 1002

Acrylonitrile Butadiene Styrene

Mitsubishi Rayon America Inc.

Message:

Shinko-Lac ABS 1002 is a standard grade of ABS that features a high modulus along with an excellent balance of rigidity, strength, processability and glossiness.

Typical applications of 1002 include communications equipment, clock accessories, trays and toys.

General Information			
Features	Good dimensional stability		
	Rigidity, high		
	Highlight		
	High strength		
	Impact resistance, good		
	Weldable		
	Workability, good		
	Sprayable		
	Machinable		
	Good chemical resistance		
	Good toughness		
	Good appearance		
	Non-toxic		
	High hardness		
Uses	Electrical/Electronic Applications		
	Shell		
	Toys		
UL File Number	E54695		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Extrusion		
	Calendering		
	Vacuum forming		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.6	g/10 min	ASTM D1238

Molding Shrinkage - Flow	0.50	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2750	MPa	ASTM D638
Tensile Strength (Yield, 23°C)	51.0	MPa	ASTM D638
Flexural Modulus (23°C, 6.35 mm)	2840	MPa	ASTM D790
Flexural Strength (Yield, 23°C, 6.35 mm)	81.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C, 6.35 mm	39	J/m	ASTM D256
0°C, 6.35 mm	59	J/m	ASTM D256
23°C, 6.35 mm	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	93.0	°C	ASTM D648
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Specific Heat	1670	J/kg/°C	ASTM C351
Thermal Conductivity	0.21	W/m/K	ASTM C177
Flammability	Nominal Value		Test Method
Flame Rating (NC)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 85.0	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	190 - 250	°C	
Middle Temperature	190 - 250	°C	
Front Temperature	190 - 250	°C	
Mold Temperature	40.0 - 80.0	°C	
Injection Pressure	68.6 - 108	MPa	
Injection instructions			

Higher mold temperature provides a product with excellent surface finish and less residual stress.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

