Braskem PE LL 5800 N

Linear Low Density Polyethylene

Braskem

Message:

LL5800N resin is a Linear Low Density Polyethylene, copolymer of octene-1, produced by solution process, for blown film extrusion with excellent mechanical properties. It contains processing aid and antioxidant additives.

General Information			
Additive	Antioxidant		
	Processing Aid		
Features	Antioxidant		
	Octene Comonomer		
Uses	Bags		
	Blending		
	Film		
	Liners		
	Packaging		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Tensile Strength		huu	ASTM D882
MD : Break, 25 µm,Blown Film	50.0	MPa	
TD : Break, 25 µm,Blown Film	40.0	MPa	
Tensile Elongation	40.0	IVIF a	ASTM D882
MD : Break, 25 µm,Blown Film	920	%	
TD : Break, 25 µm,Blown Film	1200	%	
Flexural Modulus	1200	,0	ASTM D790
1% Secant, MD : 25 μm, Blown Film	150	MPa	
1% Secant, TD : 25 µm, Blown Film	170	MPa	
Dart Drop Impact (25 µm, Blown Film)	200	g	ASTM D1709
Elmendorf Tear Strength		3	ASTM D1922
MD : 25 µm, Blown Film	330	a	
TD : 25 μm, Blown Film	770	g	
το . 25 μm, blown Film		g	

Optical	Nominal Value	Unit	Test Method
Gloss (60°, 25.0 µm, Blown Film)	121		ASTM D2457
Haze (25.0 µm, Blown Film)	8.0	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	200 to 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

