

DynaChar™ 2435-TH

Thermoplastic Polyurethane Elastomer

Polymer Dynamix

Message:

Flame Retardant TPU
Features:
Excellent Chemical Resistance
Low Temperature Properties
Good Processability
Applications:
Wire & Cable
Industrial
Automotive

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Chemical Resistance		
	Good Processability		
	Halogen Free		
	Low Temperature Impact Resistance		
	Low Temperature Strength		
	Low Temperature Toughness		
Uses	Automotive Applications		
	Industrial Applications		
	Wire & Cable Applications		
Processing Method	Injection Molding		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	14.5	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	60.7	MPa	ASTM D790
Flammability	Nominal Value		Test Method
Flame Rating (1.59 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0 to 6.0	hr	
Rear Temperature	160 to 168	°C	
Middle Temperature	166 to 174	°C	
Front Temperature	168 to 174	°C	

Nozzle Temperature	168 to 174	°C
Processing (Melt) Temp	168 to 174	°C
Mold Temperature	10.0 to 37.8	°C
Injection Pressure	68.9 to 138	MPa
Injection Rate	Moderate	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Clamp Tonnage	4.1 to 6.9	kN/cm ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

