

VITAMIDE® BI12BK9012

Polyamide 6
Jackdaw Polymers

Message:

VITAMIDE® BI12BK9012 is a Polyamide 6 (Nylon 6) product. It is available in Europe.

Characteristics include:

Flame Rated

Impact Modified

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.4	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	55.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	50	%	ASTM D638, ISO 527-2
Flexural Modulus	1800	MPa	ASTM D790, ISO 178
Flexural Stress			
--	70.0	MPa	ISO 178
Break	70.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	18	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	165	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	220	°C	ASTM D2117, ISO 1218
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257, IEC 60093
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

