

# K-vinyl KK-S-FR-A-88

Polyvinyl Chloride

Technovinyl Polymers India Ltd.

## Message:

K-vinyl KK-S-FR-A-88 is a Polyvinyl Chloride material. It is available in Africa & Middle East.

Typical application of K-vinyl KK-S-FR-A-88: Wire & Cable

General Information			
Uses	Wire & Cable Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	< 4.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	15.5	MPa	ASTM D638
Tensile Elongation (Break)	220	%	ASTM D638
Thermal	Nominal Value	Unit	
Cold Impact	No cracks		
Heat Shock	No cracks		
Thermal Stability (200°C)	2	hr	
Loss of Mass	16.0	g/m <sup>2</sup>	ASTM D573
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	30	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT