

RTP 1500-40D

Thermoplastic Elastomer, Ether-Ester

RTP Company

Message:

RTP 1500-40D is a thermoplastic elastomer, ether-ester (TEE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

General Information			
RoHS Compliance		Contact manufacturer	
Processing Method		Injection molding	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.20 - 0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	40		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	68.9	MPa	ASTM D638
Tensile Strength	3.45	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	68.9	MPa	ASTM D790
Flexural Strength	2.61	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	85	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	98	J/m	ASTM D4812
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	210 - 238	°C	
Mold Temperature	21.1 - 48.9	°C	
Injection Pressure	68.9 - 103	MPa	
Injection instructions			

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

