

Nycal™ 1850T3

Polyamide 6
Technical Polymers, LLC

Message:

Nycal™ 1850T3 is a Polyamide 6 (Nylon 6) material. It is available in North America for injection molding.
Important attributes of Nycal™ 1850T3 are:
Flame Rated
Impact Resistant

General Information			
Features	High Impact Resistance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	50.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	> 50	%	ISO 527-2
Flexural Modulus (23°C)	1700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	80	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	150	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A
Peak Melting Temperature	220	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 80.0	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	245 to 280	°C	
Mold Temperature	40.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

