

RIGITRON 10020 GF

Polycarbonate

Ovation Polymers Inc.

Message:

PC - Glass reinforced (20 %), high tensile strength, stiffness and HDT.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	High Stiffness		
	High Tensile Strength		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3600	MPa	ASTM D638
Tensile Strength ² (Break)	92.9	MPa	ASTM D638
Tensile Elongation ³ (Break)	3.5	%	ASTM D638
Flexural Modulus ⁴	5400	MPa	ASTM D790
Flexural Strength ⁵ (Yield)	132	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	67	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed, 3.20 mm	134	°C	
1.8 MPa, Annealed, 3.20 mm	129	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	1.3 mm/min		
5.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

