

Globalene® 749U

Polypropylene Impact Copolymer
Lee Chang Yung Chemical Industry Corp.

Message:

Globalene® 749U is a Polypropylene Impact Copolymer (PP Impact Copolymer) material. It is available in Asia Pacific or North America for injection molding.

Important attributes of Globalene® 749U are:

- Impact Resistant
- Copolymer
- Good Processability

Typical applications include:

- Appliances
- Automotive
- Containers

General Information			
Features	Good Moldability		
	High Impact Resistance		
	Impact Copolymer		
	Low Temperature Impact Resistance		
Uses	Appliances		
	Automotive Applications		
	Crates		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.896	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	59		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	19.6	MPa	ASTM D638
Tensile Elongation (Yield)	6.0	%	ASTM D638
Flexural Modulus	1080	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	560	J/m	ASTM D256
Unnotched Izod Impact (-18°C)	1700	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	87	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

