

Plaslube® POM HO E TL20

Acetal (POM) Homopolymer
Techmer Engineered Solutions

Message:

Plaslube® POM HO E TL20 is an Acetal (POM) Homopolymer product. It can be processed by extrusion and is available in North America. Characteristics include:
Flame Rated
Homopolymer
Lubricated

General Information			
Additive	PTFE Lubricant		
Features	Homopolymer		
	Lubricated		
Appearance	Colors Available		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	2.0	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	79		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	55.2	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2830	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	270	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	102	°C	
Melting Temperature	162	°C	
CLTE - Flow	9.9E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.57 mm)	HB		UL 94

Injection	Nominal Value	Unit
Drying Temperature	71.1	°C
Drying Time	2.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	177 to 193	°C
Middle Temperature	188 to 210	°C
Front Temperature	182 to 199	°C
Nozzle Temperature	177 to 204	°C
Processing (Melt) Temp	193 to 216	°C
Mold Temperature	82.2 to 121	°C
Injection Rate	Moderate	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	70 to 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

