

Niretan B F25 M

Polyamide 6
Soredi S.p.a.

Message:
Polyamide 6 impact modified with elastomer, reinforced with 25% glass fibre, for injection moulding

General Information				
Filler / Reinforcement	Glass Fiber,10% Filler by Weight			
Additive	Impact Modifier			
Features	Impact Modified			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.31	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 to 1.0	--	%	ASTM D955
Water Absorption				ASTM D570
23°C, 24 hr	7.0	--	%	
Equilibrium, 23°C, 50% RH	2.5	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	110	90		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength ¹ (Break)	145	85.0	MPa	ASTM D638
Tensile Elongation ² (Break)	3.5	7.0	%	ASTM D638
Flexural Modulus ³	6600	3600	MPa	ASTM D790
Flexural Strength ⁴ (Break)	200	130	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ASTM D256
-20°C, 3.20 mm	90	150	J/m	
23°C, 3.20 mm	150	200	J/m	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	190	--	°C	ASTM D648
Peak Crystallization Temperature (DSC)	220	--	°C	ASTM D3418
CLTE - Flow (23 to 55°C)	5.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+12	ohms · cm	IEC 60093
Electric Strength (1.00 mm)	34	24	kV/mm	IEC 60243-1

Relative Permittivity (1 MHz)	3.80	4.20		IEC 60250
Dissipation Factor (1 MHz)	0.020	0.12		IEC 60250
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Ignition Temperature (2.00 mm)	650	--	°C	IEC 60695-2-13
NOTE				
1.	5.0 mm/min			
2.	5.0 mm/min			
3.	1.3 mm/min			
4.	1.3 mm/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

