

4PROP® 9C13100 UV

Polypropylene Copolymer
4Plas

Message:

4PROP 9C13100 UV is a MFI 10 FR-V0 UV Stabilised Copolymer Polypropylene

General Information			
Additive	UV stabilizer		
Features	Copolymer		
	Good UV resistance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage	1.1 - 1.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1750	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	100	MPa	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	4.0	kJ/m ²	ISO 180/1A
23°C	10	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	°C	ISO 75-2/A
Melting Temperature ¹	165	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		UL 94
1.60 mm	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	20.0 - 50.0	°C	

Injection Rate	Moderate-Fast	
Holding Pressure	40.0 - 80.0	MPa
Screw Speed	400	rpm

Injection instructions

Feed Throat Temperature: 20 - 60 °CBack Pressure: Low

NOTE

1. 10 K/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT