

Razalen® P111

Polypropylene Impact Copolymer

Razin™ Engineering Plastics

Message:

Razalen P111 is a general purpose injection grade natural color impact copolymer polypropylene.

General Information			
Additive	Impact Modifier		
Features	General Purpose		
	Good Impact Resistance		
	Impact Copolymer		
	Impact Modified		
Uses	General Purpose		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.3	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27.0	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	1230	MPa	ASTM D790
Flexural Strength	31.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	9.00	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	105	°C	ASTM D648
Vicat Softening Temperature	150	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	1.0 to 2.0	hr	
Rear Temperature	200 to 210	°C	
Middle Temperature	210 to 220	°C	
Front Temperature	220 to 230	°C	
Processing (Melt) Temp	220 to 240	°C	
Mold Temperature	30.0 to 60.0	°C	
Injection Pressure	50.0 to 140	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

