

ESTALENE EN 10 SSC

Polyolefin

Cossa Polimeri S.r.l.

Message:

Estalene EN is a compounds range formulated to be used for the injection or extrusion molding of synthetic corks and it is made without SIS, SBS, SEBS rubbers. Estalene EN is patented by Cossa Polimeri.

The elastic behavior of Estalene EN is obtained with a belnd of modified polyolefins. The product is studied in order to imitate the aspects of natural cork also in its superficial defects.

To have the best performances we suggest the use of Estalene EN matched with an expanding agent (i.e. Estafoam 13 STO) that allows to obtain cells extrememly compact and very well distributed.

The cork made of Estalene EN are equivalent to the traditional ones, concerning weight, functional and aesthetic aspects. The raw material used to produce Estalene EN are suitable for food contact. Estalene EN is certified according to FDA standards.

General Information	
---------------------	--

Features	High elasticity
	Compliance of Food Exposure
Uses	Synthetic cork
Agency Ratings	FDA not rated
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Specific Gravity	0.920 - 0.940	g/cm ³	ASTM D792
------------------	---------------	-------------------	-----------

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0 - 13	g/10 min	ASTM D1238
---	----------	----------	------------

Hardness	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Hardness	80.0 - 84.0		
----------	-------------	--	--

Mechanical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Strength (Break)	> 6.00	MPa	ASTM D638
--------------------------	--------	-----	-----------

Tensile Elongation (Break)	> 500	%	ASTM D638
----------------------------	-------	---	-----------

Injection	Nominal Value	Unit
-----------	---------------	------

Hopper Temperature	140 - 150	°C
--------------------	-----------	----

Rear Temperature	145 - 155	°C
------------------	-----------	----

Middle Temperature	150 - 160	°C
--------------------	-----------	----

Front Temperature	155 - 165	°C
-------------------	-----------	----

Processing (Melt) Temp	145 - 165	°C
------------------------	-----------	----

Mold Temperature	20.0 - 40.0	°C
------------------	-------------	----

Injection Rate	Fast	
----------------	------	--

Injection instructions

Injection Pressure: according to article dimensionsPost Pressure: as low as possibleBack Pressure: average to low

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

