

McCann PP M10TCPP10

Polypropylene Copolymer

McCann Plastics Inc.

Message:

Talc Filled 10%, Polypropylene Copolymer / Lawn & Garden, Appliance, Automotive, and general purpose applications requiring medium stiffness, medium flow, and medium impact. Custom color and UV stabilized versions also available.

General Information			
Filler / Reinforcement	Talc,10% Filler by Weight		
Features	Copolymer		
	General Purpose		
	Good Flow		
	Good Impact Resistance		
	Good Stiffness		
Uses	Appliances		
	Automotive Applications		
	General Purpose		
	Lawn and Garden Equipment		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	21.4	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus - Tangent	1380	MPa	ASTM D790
Flexural Strength	26.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256
Gardner Impact	5.65	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	96.1	°C	

1.8 MPa, Unannealed	68.3	°C
Flammability	Nominal Value	Test Method
Flame Rating	HB	UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT