

omay® G21

PC Film

Suzhou OMAY Optical Materials Co., Ltd

Message:

Polished/Matte
Protective film covered on polished side

General Information			
UL File Number	E249605		
Appearance	Matte Finish		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Molding Shrinkage - Flow (150°C)	0.50 to 0.70	%	ASTM D1204
Surface Tension	> 38	mN/m	
Pencil Hardness	2B - B		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	62.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Flexural Modulus	2330	MPa	ISO 178
Flexural Stress	88.0	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	-60.0 to 125	°C	UL 746B
Brittleness Temperature	-135	°C	ASTM D746
Glass Transition Temperature	153	°C	ISO 11357-2
CLTE - Flow	5.8E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.20	W/m/K	ASTM D5470
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength	30	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
	V-2		
Flame Rating	VTM-2		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance	88.0	%	ASTM D1003
Haze	> 80	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

