

ASTAMID™ MB3EG3

Polyamide 6
Marplex Australia Pty. Ltd.

Message:

ASTAMID™ MB3EG3 is a 15% glass reinforced, heat stabilised Polyamide 6 (PA 6 or Nylon 6).
Note: The letters "U", "W" or "UV" indicate UV stabilisation has been added [ie: ASTAMID™ MA3EG5U].

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Water Absorption (Equilibrium, 23°C, 50% RH)	2.7	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	5800	MPa	ASTM D638
Tensile Strength ² (3.20 mm)	130	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	4.0	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	5300	MPa	ASTM D790
Flexural Strength ⁵ (3.20 mm)	175	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	65	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	190	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	2.0	hr	
Rear Temperature	255 to 265	°C	
Middle Temperature	265 to 275	°C	
Front Temperature	265 to 275	°C	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	50.0 to 80.0	°C	
Injection Pressure	60.0 to 130	MPa	
Injection Rate	Fast		
Back Pressure	0.100 to 0.500	MPa	
Screw Speed	40 to 60	rpm	
Clamp Tonnage	3.0 to 5.0	kN/cm ²	
NOTE			
1.	5.0 mm/min		

2.	5.0 mm/min
3.	5.0 mm/min
4.	1.3 mm/min
5.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

