

ColorFast® NY2

Polyamide 66

LTL Color Compounders, Inc.

Message:

Nylon 6,6 with or without lube

General Information			
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.5 to 2.0	%	ASTM D955
Water Absorption (24 hr)	1.3	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	82.7	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	10	%	
Break	70	%	
Flexural Modulus ³	3030	MPa	ASTM D790
Flexural Strength ⁴	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	82.2	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Shot Size	30 to 60	%	
Rear Temperature	260 to 293	°C	
Middle Temperature	266 to 293	°C	
Front Temperature	266 to 293	°C	
Nozzle Temperature	260 to 288	°C	
Processing (Melt) Temp	279 to 304	°C	
Mold Temperature	37.8 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	60 to 120	rpm	

Vent Depth	0.038 to 0.076	mm
NOTE		
1.	51 mm/min	
2.	51 mm/min	
3.	51 mm/min	
4.	51 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT