

E-RIALFILL H 15 D 20 T

Polypropylene Homopolymer

RIALTI Srl

Message:

PP homopolymer obtained by recycling of industrial scraps, 20% selected talc reinforced; additivated in order to improve the spindle flow and facilitate the detachment from the mold.
High flowability for injection molding; good mechanical properties.
Available only in the version in black color.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	Mold Release		
	Processing Aid		
Features	Good Mold Release		
	High Flow		
	Homopolymer		
Appearance	Black		
Forms	Regrind		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.3	%	
Flow	1.3	%	
Water Absorption ¹ (23°C, 24 hr)	0.020	%	ISO 62
Ash Content	20	%	ISO 3451
Accelerated Oven Aging (150°C)	6.3	day	ISO 4577
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/20
Yield, 23°C	30.0	MPa	
Break, 23°C	24.0	MPa	
Tensile Strain			ISO 527-2/20
Yield, 23°C	5.5	%	
Break, 23°C	20	%	
Flexural Modulus ² (23°C)	2500	MPa	ISO 178

Flexural Stress (23°C)	44.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength			ISO 180/1A
-20°C	2.1	kJ/m ²	
23°C	2.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	114	°C	ISO 75-2/B
1.8 MPa, Unannealed	63.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	150	°C	ISO 306/A50
--	93.0	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 335
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	190 to 210	°C	
Mold Temperature	40.0 to 50.0	°C	
Injection Rate	Fast		
NOTE			
1.	50%RH		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

