

ExxonMobil™ PP1063L1

Polypropylene Homopolymer

ExxonMobil Chemical

Message:

A homopolymer resin designed for general use. It is suitable for color master carriers and other composite modification occasions, as well as the molding of lids, cups, containers and other consumer goods.

General Information			
Uses	Cup		
	Composite		
	Shield		
	Container		
	Shell		
	Consumer goods application field		
Appearance	Natural color		
Forms	Particle		
Processing Method	Composite		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	68		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1570	MPa	ISO 527-2/1
Tensile Stress (Yield)	34.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	9.3	%	ISO 527-2/50
Flexural Modulus	1350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.6	kJ/m²	ISO 179/1eA
Notched Izod Impact (23°C)	3.1	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	85.7	°C	ISO 75-2/B
1.8 MPa, not annealed	52.3	°C	ISO 75-2/A
Vicat Softening Temperature	153	°C	ISO 306/A50
Melting Temperature (DSC)	160	°C	ISO 3146
Peak Crystallization Temperature (DSC)	113	°C	ISO 3146
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

