

# Manner Flexible PVC V961 BLK580

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

Recommended Applications: 90°C Tray Cable Jacket for applications as per UL62,1072,1277 and 1569. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information			
Uses	Cable Jacketing		
	Wire & Cable Applications		
Agency Ratings	UL 1072		
	UL 1277		
	UL 1569		
	UL 62		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35 to 1.39	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	82 to 88		
Shore A, 15 sec	77 to 83		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	13.4	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Aging	Nominal Value	Unit	
Change in Tensile Strength in Air <sup>1</sup> (121°C, 168 hr)	-7.0	%	
Change in Ultimate Elongation in Air <sup>2</sup> (121°C, 168 hr)	-3.0	%	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-40.0	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	30	%	ASTM D2863
NOTE			
1.	Air Aged Retention		
2.	Air Aged Retention		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT