

# DENYL 66 3040 MQ

Polyamide 66

Vamp Tech

Message:

PA 66, 30% mixed elastomer and glass fiber filled, not Flame Retardant compound, very good mechanical properties.

| General Information                                     |                                  |                   |                         |
|---------------------------------------------------------|----------------------------------|-------------------|-------------------------|
| Filler / Reinforcement                                  | Glass Fiber,30% Filler by Weight |                   |                         |
| Additive                                                | Impact Modifier                  |                   |                         |
| Features                                                | Impact Modified                  |                   |                         |
| Physical                                                | Nominal Value                    | Unit              | Test Method             |
| Specific Gravity                                        | 1.34                             | g/cm <sup>3</sup> | ASTM D792               |
| Molding Shrinkage                                       |                                  |                   | ASTM D955               |
| Flow                                                    | 0.40                             | %                 |                         |
| Across Flow                                             | 0.90                             | %                 |                         |
| Mechanical                                              | Nominal Value                    | Unit              | Test Method             |
| Tensile Modulus                                         | 8000                             | MPa               | ASTM D638               |
| Tensile Strength (Yield)                                | 130                              | MPa               | ASTM D638               |
| Tensile Elongation (Break)                              | 3.0                              | %                 | ASTM D638               |
| Impact                                                  | Nominal Value                    | Unit              | Test Method             |
| Notched Izod Impact Strength                            | 13                               | kJ/m <sup>2</sup> | ISO 180/A               |
| Unnotched Izod Impact Strength                          | 55                               | kJ/m <sup>2</sup> | ISO 180                 |
| Thermal                                                 | Nominal Value                    | Unit              | Test Method             |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 245                              | °C                | ASTM D648A              |
| Vicat Softening Temperature                             | 240                              | °C                | ASTM D1525 <sup>1</sup> |
| RTI Elec                                                | 130                              | °C                | UL 746                  |
| RTI Imp                                                 | 130                              | °C                | UL 746                  |
| RTI Str                                                 | 130                              | °C                | UL 746                  |
| Injection                                               | Nominal Value                    | Unit              |                         |
| Drying Temperature                                      | 90.0                             | °C                |                         |
| Drying Time                                             | 3.0                              | hr                |                         |
| Processing (Melt) Temp                                  | 280                              | °C                |                         |
| Mold Temperature                                        | 90.0                             | °C                |                         |
| NOTE                                                    |                                  |                   |                         |

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

