

Durethan® B 30 S FN40 000000

Polyamide 6
LANXESS GmbH

Message:
PA 6, non-reinforced, injection molding, halogen free flame retardant

General Information				
UL YellowCard		E245249-473615		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.14	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Across Flow : 260°C, 2.00 mm ¹	0.90	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.30	--	%	
Flow : 260°C, 2.00 mm ³	0.90	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.30	--	%	
Across Flow : 260°C, 3.00 mm ⁵	0.90	--	%	
Across Flow : 120°C, 4 hr, 3.00 mm ⁶	0.20	--	%	
Flow : 260°C, 3.00 mm ⁷	0.90	--	%	
Flow : 120°C, 4 hr, 3.00 mm ⁸	0.20	--	%	
Water Absorption				ISO 62
Saturation, 23°C	10	--	%	
Equilibrium, 23°C, 50% RH	3.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	135	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3400	1100	MPa	ISO 527-2/1
Tensile Stress				
Yield, 23°C	90.0	45.0	MPa	ISO 527-2/50
Break, 23°C	60.0	65.0	MPa	ISO 527-2/5

Tensile Strain				
Yield, 23°C	4.0	23	%	ISO 527-2/50
Break, 23°C	16	290	%	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	9.6	270	%	ISO 527-2/50
Flexural Modulus ⁹ (23°C)	3000	900	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain, 23°C	100	26.0	MPa	
23°C ¹⁰	120	35.0	MPa	
Flexural Strain at Flexural Strength ¹¹ (23°C)	5.9	8.1	%	ISO 178/A
ISO Shortname	PA 6, GFR, 14-030; ISO 1043-PA-FR (30)			ISO 1874
Residual Moisture Content	0.030 to 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	No Break	No Break		ISO 179/1eU
Notched Izod Impact Strength				ISO 180/1A
-30°C	< 10	--	kJ/m ²	
23°C	< 10	--	kJ/m ²	
Unnotched Izod Impact Strength (23°C)	No Break	No Break		ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	166	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	66.0	--	°C	ISO 75-2/A
Melting Temperature ¹²	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	9.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index ¹³ (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	V-2	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.800 mm	875	--	°C	
1.50 mm	850	--	°C	

3.00 mm	750	--	°C	
Oxygen Index ¹⁴	28	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	250 to 270		°C	
Mold Temperature	80.0 to 100		°C	

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	150x105x3mm, 80°C MT, 500 bar
6.	150x105x3mm
7.	150x105x3mm, 80°C MT, 500 bar
8.	150x105x3mm
9.	2.0 mm/min
10.	2.0 mm/min
11.	2 mm/min
12.	10°C/min
13.	Depth of Erosion: 1.60 mm
14.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT