

Zytel® 70G13L NC010

NYLON RESIN
DuPont Performance Polymers

Message:
13% Glass Reinforced Polyamide 66

General Information				
UL YellowCard		E41938-234400		
Filler / Reinforcement		Glass Fiber,13% Filler by Weight		
Additive		Lubricant		
		Mold Release		
Features		Lubricated		
Forms		Pellets		
Processing Method		Injection Molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
Part Marking Code (ISO 11469)		>PA66-GF13<		
Resin ID (ISO 1043)		PA66-GF13		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.23	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.2	--	%	
Flow	0.70	--	%	
Water Absorption				
24 hr	1.7	--	%	ASTM D570
23°C, 24 hr, 2.00 mm	7.6	--	%	ISO 62
Equilibrium, 23°C, 2.00 mm, 50% RH	2.2	--	%	ISO 62
Viscosity Number	150	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5500	3500	MPa	ISO 527-2
Tensile Stress (Break)	120	75.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	13	%	ISO 527-2
Tensile Creep Modulus				ISO 899-1
1 hr	--	3300	MPa	
1000 hr	--	2200	MPa	
Flexural Modulus	4800	2900	MPa	ISO 178
Flexural Stress	190	100	MPa	ISO 178

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	4.5	4.0	kJ/m ²	
-30°C	4.5	4.0	kJ/m ²	
23°C	5.0	6.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	30	kJ/m ²	
23°C	40	70	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-40°C	4.5	3.0	kJ/m ²	
-30°C	4.5	3.0	kJ/m ²	
23°C	4.5	4.0	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	35	28	kJ/m ²	
23°C	40	55	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	258	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	238	--	°C	ISO 75-2/A
Glass Transition Temperature ¹	80.0	--	°C	ISO 11357-2
Vicat Softening Temperature	205	--	°C	ISO 306/B50
Melting Temperature ²	262	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	4.0E-5	--	cm/cm/°C	
Transverse	9.6E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	--	ohms·cm	IEC 60093
Electric Strength	25	--	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.90	--		
1 MHz	3.20	--		
Dissipation Factor				IEC 60250
100 Hz	0.013	--		
1 MHz	0.015	--		
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (1.00 mm)	27	--	mm/min	ISO 3795

Flammability Classification				IEC 60695-11-10, -20
0.710 mm	HB	--		
1.50 mm	HB	--		
Oxygen Index	24	--	%	ISO 4589-2
Additional Information	Dry	Conditioned	Unit	Test Method
Emission of Organic Compounds	6.00	--	µgC/g	VDA 277
NOTE				
1.	10°C/min			
2.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT