

# HiPrene® HSG43HT

Polypropylene

GS Caltex

## Message:

HiPrene® HSG43HT is a glass fiber filled polypropylene compound suitable for injection moulding. This material excellent Long-Term Thermal Stability and combines good stiffness, good processability and surface finish. It has been developed especially for Automotive applications where high heat resistance is necessary. This material is available in black color.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Features	Rigid, good		
	Impact resistance, high		
	Workability, good		
	Heat resistance, high		
Uses	Application in Automobile Field		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR)	3.5	g/10 min	ISO 1133
Ash Content (600°C)	30	%	ISO 3451
Volatile Matter	0.12	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	95.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.5	%	ISO 527-2
Flexural Modulus <sup>1</sup> (23°C)	6000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.5	kJ/m <sup>2</sup>	ISO 179/1eA
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Hopper Temperature	40.0 - 80.0	°C	
Processing (Melt) Temp	210 - 250	°C	
Mold Temperature	30.0 - 50.0	°C	
Holding Pressure	4.00 - 6.50	MPa	
Injection instructions			
Back Pressure: Low to MediumScrew Speed: Low to MediumInjection Speed: 100 to 200 m/min			
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

