

MAJORIS GE460 - 6744

Polypropylene

AD majoris

Message:

MAJORIS GE460 - 6744 is a special long glass fibre reinforced polypropylene grade, for injection moulding and extrusion. The long glass fibres, chemically coupled to the polypropylene matrix, are providing with outstanding mechanical properties.

APPLICATIONS

MAJORIS GE460 - 6744 is intended for injection moulding of highly demanding technical applications.

The excellent properties of MAJORIS GE460 - 6744 make it suitable for:

Electrical components, automotive parts, interior, exterior and under the bonnet, structural furniture parts, load bearing, demanding components for various engineering sectors.

MAJORIS GE460 - 6744 can, in many of these applications, substitute other engineering plastics or metal alloys.

General Information			
Filler / Reinforcement	Long glass fiber		
Additive	heat stabilizer		
Features	Chemical coupling		
	Recyclable materials		
	Heat resistance, high		
	Thermal Stability		
Uses	Electrical components		
	Furniture		
	Metal substitution		
	Parts under the hood of a car		
	Car interior parts		
	Automotive exterior parts		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Molding Shrinkage	0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9260	MPa	ISO 527-2/1
Tensile Stress (Break)	117	MPa	ISO 527-2/50
Tensile Strain (Break)	2.8	%	ISO 527-2/50
Flexural Modulus ¹	7460	MPa	ISO 178
Flexural Stress ²	165	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	24	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	52	kJ/m ²	ISO 179/1eU
Injection	Nominal Value	Unit	
Rear Temperature	230 - 250	°C	
Processing (Melt) Temp	250 - 280	°C	
Mold Temperature	80.0 - 100	°C	
Injection Pressure	30.0 - 60.0	MPa	
Injection Rate	Slow		
Screw Speed	30 - 150	rpm	
Injection instructions			
Holding pressure: 50 to 70% of the injection pressureBack pressure: as low as possible, 0 to 10%Holding time: as long as practical			
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

