

Elastollan® 1298 A U

Thermoplastic Polyurethane Elastomer (Polyether)

BASF Polyurethanes GmbH

Message:

Highly transparent thermoplastic Polyether Polyurethane Elastomer with good hydrolysis resistance, low temperature flexibility and resistance to micro-organismus

Typical applications

Ski boot shells, ski components, Films.

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
	Hydrolysis Resistant		
	Low Temperature Flexibility		
	Microbe Resistant		
Uses	Film		
	Sporting Goods		
Appearance	Clear/Transparent		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 3 sec)	50		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	90.0	MPa	ISO 527-2
Abrasion Loss	25.0	mm ³	ISO 4649-A
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			DIN 53504
20% Strain	9.00	MPa	
100% Strain	16.0	MPa	
300% Strain	28.0	MPa	
Tensile Stress			DIN 53504
Yield ¹	50.0	MPa	
Yield	60.0	MPa	
Tensile Elongation			DIN 53504
Break ²	550	%	
Break	460	%	

Tear Strength ³	130	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	28	%	
70°C, 24 hr	45	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	170	kJ/m ²	
23°C	No Break		
Injection	Nominal Value	Unit	
Processing (Melt) Temp	215 to 240	°C	
Mold Temperature	20.0 to 70.0	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	200 to 230	°C	
NOTE			
1.	after storage in water at 80°C for 42 days		
2.	after storage in water at 80°C for 42 days		
3.	Method Bb, Angle (Nicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT