

Fenochem T 4700

Phenolic

Chemiplastica, Inc.

Message:

Colour : black
Reinforcement : wood flour/inorganic
Application areas : handles, technical pieces, housings, mounting-parts, covers
Mark : DIN 31/1549

General Information			
UL YellowCard	E177332-226447	E70218-249107	
Filler / Reinforcement	Wood Flour\Inorganic		
Features	Renewable Resource Content		
Uses	Engineering Parts		
	Handles		
	Housings		
	Protective Coverings		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Molding Shrinkage			ISO 2577
-- ¹	0.40 to 0.60	%	
--	0.60 to 0.80	%	
Water Absorption	< 100.0	mg	ISO 62
Flammability			IEC 707
Mechanical	Nominal Value	Unit	Test Method
Flexural Stress	> 70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	> 1.3	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	> 4.5	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	> 115	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+8	ohms	IEC 60093
Volume Resistivity	> 1.0E+10	ohms·cm	IEC 60093
Comparative Tracking Index	> 125	V	IEC 60112
NOTE			
1.	Post-shrink		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

