

TRANSMARE® 19HT20-0.002

Polypropylene Homopolymer

Transmare Compounding B.V.

Message:

TRANSMARE® 19HT20-0.002 is a 20% standard (gray) talc filled polypropylene homopolymer for injection molding purposes with high stiffness and good flow. Not suitable for light colors.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Features	Good Flow		
	High Stiffness		
	Homopolymer		
Appearance	Grey		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
230°C/2.16 kg	20	g/10 min	
230°C/5.0 kg	85	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	72		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/50
Yield, 4.00 mm	35.0	MPa	
Break, 4.00 mm	30.0	MPa	
Tensile Strain			ISO 527-2/50
Yield, 4.00 mm	4.5	%	
Break, 4.00 mm	15	%	
Flexural Modulus ¹	3250	MPa	ISO 178
Flexural Stress ²	50.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.2	kJ/m ²	ISO 179/A
Notched Izod Impact Strength (23°C)	2.8	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	120	°C	ISO 75-2/B
1.8 MPa, Unannealed	72.0	°C	ISO 75-2/A
Vicat Softening Temperature	153	°C	ISO 306/A

NOTE

- | | |
|----|------------|
| 1. | 2.0 mm/min |
| 2. | 2.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

