

LEXAN™ EX1332T resin

Polycarbonate

SABIC Innovative Plastics Europe

Message:

LEXAN EX1332T polycarbonate resin is designed for use in multi-wall sheet or profile extrusion applications. It contains branched polycarbonate resin, release, and is UV stabilized. It is available in a limited number of colors.

General Information	
UL YellowCard	E121562-100989271
Additive	demoulding UV stabilizer
Features	Branched polymer structure
Appearance	Available colors
Processing Method	Extrusion Sheet extrusion molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2200	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	61.0	MPa	ASTM D638
Fracture	58.0	MPa	ASTM D638
Tensile Elongation ³			ASTM D638
Yield	6.2	%	ASTM D638
Fracture	96	%	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	2330	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 50.0 mm Span)	97.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	160	J/m	ASTM D256
23°C	810	J/m	ASTM D256
Instrumented Dart Impact (23°C, Total Energy)	72.0	J	ASTM D3763

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.20mm	141	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	131	°C	ASTM D648

Vicat Softening Temperature			
--	146	°C	ASTM D1525 ⁶
--	148	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	6.5E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	6.8E-5	cm/cm/°C	ASTM E831
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm, Testing by SABIC)	HB		UL 94
Extrusion instructions			

Multiwall Sheet Extrusion Parameters:
 Adapter Temperature: 240 - 280 C
 Barrel - Zone 1 Temperature: 260 - 300 C
 Barrel - Zone 2 Temperature: 260 - 290 C
 Barrel - Zone 3 Temperature: 260 - 290 C
 Calibrator Temperature: 50 - 100 C
 Die Temperature: 240 - 300 C
 Drying Temperature: 120 C
 Drying Time: 2 - 4 hrs
 Hopper Temperature: 100 - 120 C
 Melt Temperature: 260 - 300 C

NOTE	
1.	5.0 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	1.3 mm/min
5.	1.3 mm/min
6.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT