

KOPLA PA66 KDG1133CR

Polyamide 66

KOPLA Co., Ltd.

Message:

KOPLA PA66 KDG1133CR is a Polyamide 66 (Nylon 66) material filled with glass fiber. It is available in Asia Pacific.

Important attributes of KOPLA PA66 KDG1133CR are:

Flame Rated

Chemical Resistant

Typical applications include:

Automotive

Electrical/Electronic Applications

Tanks

General Information	
Filler / Reinforcement	Glass Fiber
Features	Good Chemical Resistance
Uses	Automotive Exterior Parts
	Automotive Under the Hood
	Electrical Parts
	Electrical/Electronic Applications
	Tanks

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 to 0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	177	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.5	%	ASTM D638
Flexural Modulus (23°C)	8830	MPa	ASTM D790
Flexural Strength (23°C)	245	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	255	°C	
1.8 MPa, Unannealed	240	°C	
Melting Temperature	260	°C	
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	25	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

